

EXCELLENT CYCLING ABILITY FOR



GL-12110

ADVANCED TECHNOLOGY

GELLED VALVE REGULATED LEAD ACID BATTERY (GVR) FOR CYCLING APPLICATIONS

12V 110AH @ 20 HR RATE to 1.75VPC 12V 120AH @ 100 HR RATE to 1.75VPC

LONG DURATION

TELECOMMUNICATION
SOLAR / PHOTOVOLTAIC
WIND GENERATION
MARINE
APPLICATIONS


Innovative Features

- Deep cycle battery designed, GEL electrolyte with highly porous glass micro-fiber separator;
- Exceptional energy storage capacity combined with long life BCI Classification:
- Thick positive plate design for maximum service float life 12 years design life @ 20°C(68°F);
- ◆ Thickness positive plate plus optimized plate alloy to anti-corrosion;
- Maintenance-free (no topping up) during the whole service life due to EverExceed GEL technology;
- Proprietary Fixed Orifice Plate Pasting technology applying active materials on both sides of the grid for consistent cell-to-cell performance, higher capacity and uniform grid protection;
- ◆ Flame-arresting one-way pressure-relief vent for safe and long life;
- Electrolyte in solid gel form will not stratify no equalization charge required;
- Sulfuric acid thixotropic gel, gel powder from Europe leading supplier to ensure the unique performance of gel battery;
- ◆ Increased durability and deep cycle ability for heavy duty applications;
- Fully tank formed grid Lead Calcium Tin plate ensures voltage matching between cells;
- Shelf life up to 2 years at 20°C (68°F), very low gassing due to internal gas recombination;
- Can be used in any orientation. Upright, side or end mounting recommended;
- Unique performance against high temperature;
- UL Recognized component;
- ◆ Spill-proof and leak-proof.


	12 VOLTS - 110 AMPERE HOUR @ 20 HOUR RATE											
	AH Capacity to 1.75VPC @ 20°C (68°F)											
End Point Volts/Cell	1.5hr	2hr	3hr	4hr	5hr	8hr	10hr	12hr	20hr	24hr	100hr	
1.75	76.2	76.6	81.8	85.9	88.6	97.1	101	102	110	114	120	


Gellyte Range VRLA














Length: 305mm Width: 168mm Height: 215mm

Electrical Specifications										
Cells Per Unit	Voltage Per Unit	Weight	Electrolyte	Short Circuit Current	Internal Resistance Milliohms					
6	12.84	63.8lbs 29.0kg	SG = 1.300	2958 Amps	3.8					

Capacity	2V 110AH @ 20 HR RATE to 1.75VPC 12V 120AH @ 100 HR RATE to 1.75VPC
Applicable Operating Temperature Range	-40°C (-40°F) to +70°C (158°F).
Ideal Operating Temperature Range	+20°C (+68°F) to +32°C (90°F).
Floating Charging Voltage	13.5 to 13.8 VDC/unit Average at 20°C (77°F).
Recommended Maximum Charging Current Limit	22.0 Amperes (0.20 C20 Amperes)
Equalization and Cycle Service Charging Voltage	14.1 to 14.4 VDC/unit Average at 20°C (77°F).
Maximum AC Ripple (Charger)	0.5% RMS or 1.5% P-P of float charge voltage recommended for best results. Maximum voltage allowed = 1.4% RMS (4% P-P). Maximum current allowed = 0.55 amperes RMS (C/20) to 1.75VPC.
Self Discharge	EverExceed Gellyte Range batteries may be stored for up to 24 months at 20°C (68°F) and then a freshening charge is required. For higher temperatures the time interval will be shorter.
Accessories	Inter unit connectors racks and cabinet systems are available.
Terminal: Inserted	Threaded copper alloy insert terminal.
Terminal Hardware Initial Torque: Inserted Terminal	9 N-m

Constant Power Discharging Ratings - Watts Per Cell @ 20°C (68°F)												
End Point Volts/Cell	1.5hr	2hr	3hr	4hr	5hr	8hr	10hr	12hr	20hr	24hr	100hr	
1.85	87.8	68.4	49.2	39.0	32.2	22.3	18.4	15.9	10.6	8.63	2.38	
1.80	95.4	71.9	51.5	40.8	33.9	23.2	19.4	16.5	10.7	9.13	2.46	
1.75	115	91.6	64.5	51.2	42.4	29.3	24.4	20.7	13.4	11.5	3.14	

	Constant Current Discharging Ratings - Amperes Per Cell @ 20°C (68°F)												
End Point Volts/Cell	1.5hr	2hr	3hr	4hr	5hr	8hr	10hr	12hr	20hr	24hr	100hr		
1.85	44.0	35.3	25.1	19.8	16.3	11.1	9.17	7.94	5.15	4.42	1.14		
1.80	47.6	37.4	26.7	20.9	17.3	11.8	9.79	8.31	5.33	4.56	1.18		
1.75	50.8	38.3	27.2	21.5	17.7	12.1	10.1	8.54	5.50	4.78	1.20		

Note: Batteries to be mounted with 0.39 in (1.00 cm) spacing minimum and free air ventilation. Specifications subject to change without notification.