






SEALED RECHARGEABLE LEAD ACID BATTERY

Dimensions and Terminal



AINO MICRO Range VRLA

Innovative Features

- 5~8 years design life @ 20°C(68°F) ambient temperature, 80% remaining capacity;
- E UL Recognized component;
- ➡ Rechargeable VRLA batteries with an electrolyte retained in a glass mat with a very fine glass fibre structure.
- High-Compression Absorbed Glass Mat technology (AGM) for over 99% recombination efficiency.
- Proprietary Fixed Orifice Plate Pasting technology applying active materials on both sides of the grid for consistent cell-to-cell performance, higher capacity and uniform grid protection.
- Perfect combination between energy storage performance and reliability;
- Derates at a low internal pressure;
- □ Low self-discharge rate (less than 3% / month @ 20°C(68°F);
- Grid plate construction consisting of a Lead Calcium Tin alloy;
- High impact resistant ABS resin cases and covers;
- Available in V-0 Flame Retardant Material;
- In compliance with IEC 896-2;
- 🖼 Wide operating temperature range;
- Sealed construction for operation in any position.

Performance Specifications

Normal Voltage	12V	
Normal Capacity	20 hour rate (40.0 mA to 10.5 volts): 0.80 Ah 10 hour rate (72.0 mA to 10.5 volts): 0.72 Ah 5 hour rate (130 mA to 10.2 volts): 0.65 Ah 1 hour rate (480 mA to 9.00 volts): 0.48 Ah	
Internal Resistance	150 milliohms	
Approximate Weight	0.35 kg (0.77 lbs)	
Applicable Operating Temperature Range	-40°C(-40°F) to +70°C (+158°F)	
Ideal Operating Temperature Range	+20°C (+68°F) to +28°C (+82.4°F)	
Charge Retention (Shelf Life) at 68°F(20°C)	1 month 3 month 6 month	97% 91% 85%
Standby Service	8 years	
Cycle Service	100% depth of discharg 50% depth of discharge 30% depth of discharge	650 cycles
Standard Terminals	Wire Leads & Plug	









www.everexceed.com


Copyright © EverExceed Corporation. All rights reserved.


AINO MICRO Range VRLA




















Copyright © EverExceed Corporation. All rights reserved.

www.everexceed.com